



UNIVERSITI PUTRA MALAYSIA

**STRUCTURAL BEHAVIOUR OF INTERLOCKING HOLLOW BLOCK
CONCRETE WALL WITH SUBJECTED TO AXIAL AND ECCENTRIC
LOADS**

LABEED AHMED MOHAMED AL-QAATABI.

FK 2008 28

**STRUCTURAL BEHAVIOUR OF INTERLOCKING HOLLOW BLOCK
CONCRETE WALL WITH OPENING SUBJECTED TO AXIAL AND
ECCENTRIC LOADS**

BY

LABEED AHMED MOHAMED AL-QAATABI

**Thesis Submitted to the School of Graduate Studies, University Putra Malaysia, In
Partial Fulfillment the Requirement for the Degree of Master of Science**

June 2008



Abstract of thesis presented to the senate of Universiti Putra Malaysia
in fulfillment of the requirement for the degree of Master of Science.

**STRUCTURAL BEHAVIOUR OF INTERLOCKING HOLLOW BLOCK
CONCRETE WALL WITH OPENING SUBJECTED TO AXIAL AND
ECCENTRIC LOADS**

By

Labeed Ahmed Mohamed

June 2008

Chairman: Professor Waleed A. M. Thanoon, Phd

Faculty: Engineering

The use of structural masonry may result in cheaper and faster construction of structures compared with the conventional approach of framed building construction. In Malaysia the supply of houses by both public and private is still far from meeting the demand especially in low cost housing sector. Hence the search for fast, safe and economical masonry system becomes a necessity to meet the demand for housing in Malaysia. Interlocking block system is promoted, as a new building technique that may result to more economical construction. The main concept of interlocking hollow block system is the elimination of the mortar layers and instead the blocks are interconnected through providing key connection (protrusion and groove). The use of interlocking load bearing hollow blocks in building construction will speed up the construction process as a result of the elimination of mortar layers. Furthermore, due to the self-aligning features of the interlocking hollow blocks, the walls can be assembled much faster by unskilled workers compared to mortar masonry construction.

Putra block is an interlocking block system used in the construction of load bearing wall (Waleed et al.(2005)). The structural behavior of the walls constructed using Putra block was presented by Jaafar et al. (2006) and Waleed et al. (2007). The structural behavior of interlocking hollow blocks load bearing wall is not fully explored due limited research on its structural response under the applied load till failure. Moreover, the effect of window opening on the structural response of the interlocking wall especially on the stress distribution in the wall and its failure mechanism are not yet addressed and require special attention for safe and accurate design of walls.

This study presents experimental testing of interlocking hollow block walls having window opening under concentric and eccentric vertical compressive load. The experimental testing focuses on the effect of different layout of the reinforced stiffener around the opening on the structural response of the wall and its failure mechanism.

Eight wall panels having dimension of 1.5 m x 1.6 m (length x height) with a rectangular opening occupying 20% of the wall area were assembled using Putra block. The specimens are differing in the layout of reinforced stiffener around the opening. These wall specimens were subjected to a vertical load of 0 mm, 40 mm, and 55 mm eccentricities. The response was investigated in terms of deformation characteristics, strain variation, failure load and failure mechanism.

The results indicate that the responses of interlocking hollow block wall with opening are similar to the bonded masonry system. The presence of window opening

of an area equal to 20% of the surface area of the wall may reduce the axial efficiency of the interlocking wall up to 50% of the solid wall capacity. Furthermore, the layout of the stiffeners plays a significant effect in the structural response of the interlocking wall and leads to completely different failure mechanism of the wall.

Abstrak tesis yang dikemukakan kepada senat universiti Putra Malaysia sebagai
memenuhi keperluan untuk ijazah master sains

**KELAKUAN STRUKTUR DINDING KONKRIT BLOK BERONGGA
BERKUNCI DENGAN BUKAAN DI BAWAH BEBANAN PAKSI DAN SIPI**

Oleh

Labeed Ahmed Mohamed

Jun 2008

Pengerusi; Professor Waleed A. M. Thanoon, PhD

Fakulti: Kejuruteraan

Pergunaan masonri struktur membolehkan pembinaan struktur yang lebih murah dan cepat jika dibandingkan dengan pendekatan tradisional pembinaan bangunan berangka. Di Malaysia, pembinaan rumah oleh sektor awam dan swasta masih belum memenuhi permintaan terutama di dalam sektor perumahan kos rendah. Oleh itu, pencarian untuk sistem masonri yang cepat, selamat dan ekonomi menjadi satu keperluan untuk memenuhi permintaan perumahan di Malaysia. Pengenalan kepada sistem blok berkunci sebagai teknik bangunan baru yang dapat menyumbang kepada pembinaan lebih berekonomi. Konsep utama sistem blok berongga berkunci ialah penyingkiran lapisan mortar dan sebaliknya blok adalah disambung berterusan melalui hubungan kunci (unjuran dan liang). Penggunaan blok berongga berkunci dalam pembinaan bangunan akan mempercepatkan pembinaan akibat penyingkiran lapisan mortar. Tambahan pula, disebabkan blok berongga berkunci yang boleh memadan antara sendiri, dinding boleh dibina dengan lebih cepat oleh pekerja tidak mahir jika dibandingkan dengan pembinaan masonri mortar.

Blok Putra ialah sistem blok berkunci yang digunakan dalam pembinaan dinding tahanan bebanan (Waleed et.al, 2005) kemudian struktur dinding yang dibina dengan blok Putra telah dikaji oleh (Jaafar et. al, 2006) dan (Waleed et al. 2007). Kemudian struktur dinding tahanan bebanan blok berongga berkunci masih belum lagi dikaji sepenuhnya disebabkan kajian terhadap ke atas tindakbalas struktur di bawah bebanan khidmat sehingga kegagalan. Tambahan pula, kesan bukaan tingkap ke atas tindakbalas struktur dinding berkunci terutama yang melibatkan agihan tekanan di dalam dinding dan mekanisme kegagalannya masih belum lagi diberi perhatian dan ini memerlukan perhatian khas bagi rekabentuk dinding yang selamat.

Kajian ini mengenai ujian secara eksperimen ke atas dinding blok berongga berkunci yang mempunyai bukaan tingkap di bawah bebanan mampatan paksi dan sili. Ujian secara eksperimen memberi tumpuan kepada kesan pelbagai susunan pengukuh meneguhkan di sekeliling bukaan ke atas tindakbalas struktur dinding dan mekanisme kegagalannya.

Lapan panel dinding berdimensi 1.5m x 1.6m (panjang x tinggi) dengan bukaan segiempat tepat yang memenuhi 20% keluasan dinding telah dipasang dengan blok Putra. Spesimen adalah berbeza dari segi susunan pengukuh di sekeliling bukaan. Spesimen dinding ini telah didedahkan kepada bebanan menegak dengan kesipian 0 mm, 40 mm dan 55 mm. Tindakbalas telah dikaji dari segi ciri kegagalan, variasi ketegangan, bebanan gagal dan mekanisme kegagalan.

Keputusan eksperimen menunjukkan tindakbalas dinding blok berongga berkunci dengan bukaan adalah sama dengan sistem masonry terikat. Kehadiran bukaan

tingkap dengan keluasan 20% daripada luas mukaan dinding mungkin mengurangkan kecekapan paksi dinding berkunci sehingga 50% kapasiti dinding tanpa bukaan. Tambahan pula susunan pengukuh memainkan kesan signifikan di dalam tindakbalas struktur dinding berkunci dan membawa kepada mekanisme kegagalan dinding yang berlainan sama sekali.

ACKNOLDGEMENT

In The Name of Allah Most Gracious Most Merciful

Alhmdulillah Rab alalameen who helps me to achieve my thesis. In this occasion I would like to express my deep thanks and gratitude to Prof. Dr. Waleed A. Thanoon and Prof. Dr. Mohd Saleh B. Jaafar for their valuable help and encouragement they introduced it to me during their supervision. I will keep remembering their kind treatment and valuable advice.

My deep thanks to Prof Dr. Jamaloddin Noorzaei for his help.

In this occasion great thanks should be express for the member of the examination committee who spent their valuable time in reading my thesis and evaluate it.

Thanks to structural laboratory staff for their assistance.

I would like to express my deep gratitude to my parents, wife and brother for their kind support.

I certify that an Examination Committee has met on 17 June 2008 to conduct the final examination of Labeed Ahmed Al-qaatabi on his Master of Science thesis entitled “Structural Behavior of Interlocking Hollow Block Concrete Wall with Opening Subjected to Axial and Eccentric Loads” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the student be awarded the Master of Science.

Members of the Examination Committee were as follows:

Mohd Amran Mohd Salleh, PhD

Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Ir. Abang Abdullah Abang Ali


Professor
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Ir. Salihudin Hassim

Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Taksiah A. Majid, PhD

Associate Professor
Faculty of Engineering
Universiti Sains Malaysia
(External Examiner)


HASANAH MOHD GHAZALI, PhD
Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 26 August 2008

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were as follows:

Waleed A. M. Thanoon, PhD


Professor
Faculty of Engineering
University Putra Malaysia
(Chairman)

Mohd Saleh B. Jaafar, PhD

Associate Professor
Faculty of Engineering
University Putra Malaysia
(Member)

Jamaluddin Noorzae, PhD

Associate Professor
Faculty of Engineering
University Putra Malaysia
(Member)




AINI IDERIS, PhD
Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 11 September 2008

DECLARATION

I declare that the thesis is my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously, and is not concurrently, submitted for any other degree at Universiti Putra Malaysia or at any other institution.

A handwritten signature in blue ink, reading 'Labeed gahabi', is written over a horizontal line. The signature is stylized and includes a long horizontal stroke extending to the right.

LABEED AHMED MOHAMED

Date: 12/8/2008

TABLE OF CONTENTS

	Page
ABSTRACT	ii
ABSTRAK	v
ACKNOWLEDGEMENTS	viii
APPROVAL	ix
DECLARATION	x
LIST OF TABLES	xiii
LIST OF FIGURES	xiv
LIST OF ABBREVIATIONS	xvii
 CHAPTER	
 1 INTRODUCTION	
1.1 Introduction	1-1
1.2 Problem Statement	1-2
1.3 Objectives	1-2
1.4 Synthesis	1-3
1.5 Layout of Thesis	1-3
 2 LITERATURE REVIEW	
2.1 Introduction	2-1
2.2 Conventional Block System	2-2
2.2.1 Prism	2-2
2.2.2 Wall Panel	2-10
2.3 Interlocking Hollow Block System	2-21
2.3.1 Prisms	2-21
2.3.2 Interlocking Wall Panels	2-26
2.4. Shear Wall	2-37
 3 METHODOLOGY	
3.1 Introduction	3-1
3.2 Interlocking Hollow Block	3-1
3.3 Materials and Equipments	3-4
3.3.1 Materials	3-4
3.3.2 Equipments	3-5
3.4 Computer Analysis	3-5
3.5 Experimental Program	3-8
3.5.1 Individual Block	3-8
3.5.2 Prism	3-10



3.5.3	Wall Panel	3-11
4	RESULTS AND DISCUSSION	
4.1	Introduction	4-1
4.2	Individual Block Strength	4-1
4.3	Water Absorption	4-6
4.4	Prism Test	4-7
4.5	Structural Behavior of Interlocking Block Walls	4-10
4.5.1	Compressive Strength	4-11
4.5.2	Deformation Characteristics	4-14
4.5.3	Load Strain Relation	4-21
4.5.4	Failure Mode of Panels	4-41
4.5.5	Load Steel Strain Relation	4-54
5	CONCLUSIONS	
5.1	General	5-1
5.2	Recommendation for the future work	5-3
	REFERENCES	R-1
	APPENDICES	A-1
	BIODATA OF THE STUDENT	
	LIST OF PUBLICATIONS	

LIST OF TABLES

Table		Page
3.1	The physical properties of Putra block.	3-2
3.2	Materials description	3-5
3.3	Shown the Size of Each Model and the Different in the Stress	3-9
3-4	Group Specimens	3-12
4.1	The Ratio of the Compressive Strength of the Prism to the Individual Block Unit Different Prism	4-8
4.2	Comparison between the Strength of the Panels	4-12

LIST OF FIGURES

Figures	Page
2.1 Single-Block Specimens and Two- and Three-Block Prisms Tested.	2-3
2.2 Modes of Failure for Unfilled Single-Block Specimens	2-4
2.3 Modes of Failure for Filled Single-Block Specimens	2-4
2-4 Modes of Failure for: (a) Unfilled Three-Block Prism Compressed Normal to Bed Face; (b) Unfilled Two-Block Prism Compressed Parallel to Bed Face	2-6
2.5 Modes of Failure for: (a) Filled Three-Block Prism Compressed Normal to Bed Face; (b) Filled Two-Block Prism Compressed Parallel to Bed Face	2-7
2.6 Failure Modes for Hollow Concrete Masonry Prisms: (a) Strong Mortar; (b) Weak Mortar	2-9
2.7 Summary of Waffle and Loading Type	2-10
2.8 Linear Potentiometer Displacement Transducer (LPDT) Arrangements for Series 1 Test	2-12
2.9 Typical web splitting Occurred in the Hollow Blocks beneath the Bond Beam	2-13
2.10 Typical Failure Mode of Waffle under Eccentric Concentrated Load ($e = 64 \text{ mm}$)	2-14
2.11 Vertical Cracking and Face-Shell Spalling of Waffle under Concentric Concentrated Load on the end column (Plate length = 160 mm)	2-15
2.12 Local Crushing-Splitting of Waffle under Concentric Concentrated Load on the End Column (Plate Length = 80 mm)	2-15
2.13 Failure Mode of Waffle under Eccentric Concentrated Load on the End Column ($e = 32 \text{ mm}$, Plate Length = 160 mm).	2-16
2.14 Failure Modes of Waffle under Concentrated Load on the Middle Column: (a) Concentric; (b) Eccentric, $e = 32 \text{ mm}$; and (c) Eccentric, $e = 64 \text{ mm}$	2-17
2.15 The Specimens in the Layout of the Stiffeners	2-19
2.16 Compressive Stress-Strain Curves of Masonry Prisms	2-23



2.17	Typical Cracks in Masonry Prisms	2-23
2.18	Failure Mode for Putra Block Prisms	2-24
2.19	Cross-Section of the Wall Specimens	2-25
2.20	Test Set-up for Concentrated Axial Load Test	2-26
2.21	Test Set-up for Transverse Load Test	2-26
2.22	Cracks due to the uneven bed surfaces of the units	2-27
2.23	Different Layouts of Tested Wall Specimens	2-29
2.24	Comparison between Bounded and Unbounded Walls	2-30
2.25	Reduction Factors Due to Eccentric Load in Bounded and Unbounded Walls	2-30
2.26	Crack Patterns of Un-stiffened Wall Specimens at Failure	2-32
2.27	Crack Patterns of Selected Wall Specimens in Group B at Failure	2-33
2.28	Crack Patterns of Selected Wall Specimens in Group C at Failure	2-34
2.29	Full-scale wall for laboratory tests with wall dimensions	2-34
2.30	Crack pattern in a non-plastered wall (a) and in a plastered wall	2-36
3.1	Different Types of Putra interlocking Hollow Block	3-2
3.2	Details of the Different Units of Putra Block	3-4
3.3	Stress Distribution of the Full Scale Model	3-6
3.4	Stress Distribution of the Model 1	3-7
3.5	Stress Distribution of the Model 2	3-7
3.6	Stress Distribution of the Model 3	3-8
3.7	Interlocking Block in the Compression Testing Machine	3-10
3.8	Prism	3-11
3.9	The Position of the Stiffener in Each Group	3-13
3.10	The Test Setup for the Experimental Testing of the Wall Panels	3-15
3.11	The Boundary Condition at the Bottom of the Wall Panels	3-16

3.12	The Boundary Condition at the Top of the Wall Panels	3-16
3.13	The Position of the Dial Gauge for Determine the Vertical Deformation	3-17
3.14	The Position of the LVDT and Dial Gauge at the top of the Wall Panel	3-18
3.15	The Position of the LVDT and Dial Gauge at the Bottom of the Wall Panel	3-18
3.16	The Arrangement of the Strain Gauges on the Wall Panel	3-19
4.1	Variation of Strength with Weight for Stretcher Unit	4-2
4.2	Variation of Strength with Weight for Corner Unit	4-2
4.3	Variation of Strength with Weight for Half Unit	4-3
4.4	The Normal Distribution Curve for the Different Types of Putra Block Unit	4-4
4.5	Splitting Failure for the Stretcher Unit	4-5
4.6	Crushing Failure for the Stretcher Unit	4-5
4.7	Prism	4-8
4.8	Failure Mode of Un-grouted Prisms	4-9
4.9	Failure Mode of Grouted Prisms	4-10
4.10	Variations of Wall Panel Efficiency due to Eccentricity and Stiffener Effect for Group A and Group D	4-12
4.11	The Effect of the Opening on the Efficiency of the Wall Panel	4-13
4.12	Lateral Deformation at Load 91 KN	4-14
4.13	Lateral Deformation of Group A at the Failure Load	4-15
4.14	Lateral Deformation of Group D at the Failure Load	4-16
4.15	Lateral Deformation of Wall Panels, Group A	4-17
4.16	Lateral Deformation of Wall Panels, Group D	4-17
4.17	Vertical Deformation of Wall Panels with $e = 0.0$ mm	4-18
4.18	Vertical Deformation of Wall Panels With $e = 40$ mm	4-19

4.19	Vertical Deformation of Wall Panels with $e = 55 \text{ mm}$	4-20
4.20	Load Strain Relation for Panel A1	4-23
4.21	Load Strain Relation for Panel B1	4-25
4.22	Load Strain Relation for Panel C1	4-28
4.23	Load Strain Relation for Panel D1	4-30
4.24	Load Strain Relation for Panel A2	4-33
4.25	Load Strain Relation for Panel D2	4-35
4.26	Load Strain Relation for Panel A3	4-38
4.27	Load Strain Relation for Panel D3	4-40
4.28	The Failure Mode of Wall A1 at Different Load Stage	4-42
4.29	The Failure Mode of Wall B1 at Different Load Stage	4-46
4.30	The Failure Mode of Wall C1 at Different Load Stage	4-47
4.31	The Failure Mode of Wall D1 at Different Load Stage	4-48
4.32	The Failure Mode of Wall A2 at Different Load Stage	4-49
4.33	The Failure Mode of Wall A3 at Different Load Stage	4-50
4.34	The Failure Mode of Wall D2 at Different Load Stage	4-51
4.35	The Failure Mode of Wall D3 at Different Load Stage	4-52
4.36	Stress Strain Relation for the Top Horizontal Stiffener, Wall Panel A1	4-55
4.37	Stress Strain Relation for the Top Horizontal Stiffener, Wall Panel A2	4-55
4.38	Stress Strain Relation for the Top Horizontal Stiffener, Wall Panel A3	4-56
4.39	Stress Strain Relation for the Top Horizontal Stiffener, Wall Panel B1	4-57
4.40	Stress Strain Relation for the Bottom Horizontal Stiffener, Wall Panel B1	4-57
4.41	Stress Strain Relation for the Top Horizontal Stiffener, Wall Panel C1	4-58

4.42	Stress Strain Relation for the Vertical Stiffener, Wall Panel C1	4-59
4.43	Stress Strain Relation for the Top Horizontal Stiffener, Wall Panel D1	4-60
4.44	Stress Strain Relation for the Bottom Horizontal Stiffener, Wall Panel D1	4-60
4.45	Stress Strain Relation for the Vertical Stiffener, Wall Panel D1	4-61
4.46	Stress Strain Relation for the Top Horizontal Stiffener, Wall Panel D2	4-61
4.47	Stress Strain Relation for the Bottom Horizontal Stiffener, Wall Panel D2	4-62
4.48	Stress Strain Relation for the Vertical Stiffener, Wall Panel D2	4-62
4.49	Stress Strain Relation for the Top Horizontal Stiffener, Wall Panel D3	4-63
4.50	Stress Strain Relation for the Bottom Horizontal Stiffener, Wall Panel D3	4-63
4.51	Stress Strain Relation for the Vertical Stiffener, Wall Panel D3	4-64

ABBREVIATION

W_s	saturated weight of specimen, kg,
W_d	dry weight of specimen, kg,
W_l	lab environment weight of specimen, kg
V_n	net volume of specimen, m^3
f_b	compressive strength of the block, N/mm^2
f_p	compressive strength of the prism, N/mm^2
e	eccentricity of the load, mm
t	thickness of the wall, mm

CHAPTER I

INTRODUCTION

1.1 Introduction

Interlocking hollow block masonry systems were developed recently to reduce the construction time of traditional bonded masonry system. The main feature of interlocking hollow block masonry system is the replacement of mortar layer commonly used in bonded masonry with interlocking keys (protrusion and grooves).

The interlocking hollow block masonry system has self-aligning features enabling easy assemblage by unskilled workers. Furthermore, the elimination of mortar layers will reduce the cost, construction time and enhance the structural behavior compared to traditional masonry system.

Putra block is an interlocking hollow block masonry system used in the construction of load bearing wall. It was developed by Housing Research Centre at UPM (Waleed et al. (2005)). The structural behavior of prisms, small wall panel constructed by using Putra blocks system was presented by Jaafar et al.(2006).

Extensive research has been carried out to investigate the compressive strength of the system under concentric and eccentric loading using, individual blocks, prisms, walls. Shear characteristic of the system have been investigated using a

modified triplet test setup under different pre-compression loads. Full scale walls were assembled using Putra block and tested under axial eccentric loads by Waleed et al. (2007). Furthermore, finite element programmed was developed and used to study the structural behaviour of interlocking hollow block system (Walled et al.(2007)).

1.2 Problem Statement

The above experimental and theoretical analyses of interlocking hollow block masonry system using Putra blocks showed that the structure response of interlocking hollow block masonry system is similar to traditional bonded masonry system. However, the effect of window opening on the structural response of the Putra block interlocking hollow block masonry system was not yet addressed and investigated. It requires a special attention for safe, accurate and economical design of the system. This study presents experimental testing of interlocking hollow block walls having window opening under axial and eccentric vertical load.

1.3 Objectives

1. To determine the structural response of interlocking hollow block masonry wall having window opening using Putra block under axial and eccentric vertical load.

2. To determine the effect of different layouts of stiffeners around the window opening on the structural behavior of the interlocking hollow block masonry system.

1.4 Scope and Limitations

The following are the scope of this research:

- 1- The structural response are evaluated based on the deformation characteristic, stress distribution, failure load, and failure mechanism of interlocking hollow block wall with opening.
- 2- The behaviours are based on tested on three different eccentricities i.e. 0 mm, 40 mm, and 55 mm on the interlocking hollow block walls with opening as well as with and without stiffeners.
- 3- Only wall with dimension 1.6 m x 1.5 m were tested in the experimental work.
- 4- The load subjected vertically to the wall panel.

1.5 Layout of Thesis

The thesis is divided into five chapters as follows:

Chapter one: Presents problem's definition, scope and objectives of the study.

Chapter two: Discuss the critical literature review on interlocking blocks and traditional masonry.

Chapter three: highlight the experimental work of the research with computer analysis for the size specimens.

Chapter four: highlight the out come of the result of the experimental work.

Chapter five: highlight the reached conclusion of the research and the recommendation for the future work.